

IN THE CLAIMS:

The following is a complete listing of claims in this application.

1. (currently amended) A hard wood strand product including substantially aligned strands of one or more eucalypts bonded together with a binder including an isocyanate ~~or phenolic~~ resin.

2. (original) A product as in claim 1 wherein the eucalypts are selected from the species such as Bluegum (E. Globulus), Karri (E. Diversicolor), Sydney Bluegum (E. Saligna), Marri (E. Calophylla) or Jarrah (E. Marginata).

3. (original) A product as in claim 1 wherein the binder is a polymeric methane di-isocyanate resin and includes a wax.

4. (original) A product as in claim 1 wherein the strands have an average length between 145 mm and 180 mm.

5. (original) A product as in claim 1 wherein the strands have an average width of about 10 to 25 mm.

6. (original) A product as in claim 1 wherein the strands have an average thickness between 0.5 mm and 1.5 mm.

7. (original) A product as in claim 1 wherein at least 70% of the strands are fully aligned.

8. (original) A product as in claim 1 having a density of between 600 kg/m³ to 850 kg/m³.

9. (original) A product according to claim 1 which is a lumber or board product.

10. (original) A product according to claim 1 having a modulus of elasticity $\geq 14,000$ N/mm².